

PPA, excellent high temperature resistance, strength, rigidity, dimensional stability, heat stabilized and hydrolysis resistance.

Properties	Typical Value	Units	Test Method
Mechanical Properties			
	dry / cond.		
Tensile Modulus, 1 mm/min	13000 / 13000	MPa	ISO 527-1/-2
Tensile Stress at Break, 50 mm/min	240 / 210	MPa	ISO 527-1/-2
Tensile Strain at Break, 50 mm/min	2 / 2.5	%	ISO 527-1/-2
Flexural Modulus, 2 mm/min	12000 / 12000	MPa	ISO 178
Flexural Strength, 2 mm/min	350 / 290	MPa	ISO 178
Charpy Notched Impact Strength, +23°C	10 / 9	KJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	9 / 9	KJ/m ²	ISO 179/1eA
Thermal Properties			
Melting Temperature, 10°C/min	300	°C	ISO 11357-1/-3
Temperature of Deflection Under Load, 1.8 MPa	280	°C	ISO 75-1/-2
Temperature of Deflection Under Load, 0.45 MPa	290	°C	ISO 75-1/-2
Flame Resistant, 1.5 mm	HB	Class	UL 94
Electrical Properties			
	dry / cond.		
Relative Permittivity, 1 MHz	4.4 / 4.6	-	IEC 62631-2-1
Volume Resistivity	1E15 / 1E15	Ohm.m	IEC 62631-3-1
Surface Resistivity	1E14 / 1E15	Ohm	IEC 62631-3-2
Physical Properties			
Density	1.57	g/cm ³	ISO 1183
Molding Shrinkage, 2.0 mm, Parallel / Normal	0.3 / 0.8	%	ISO 294-4
Humidity Absorption, 23°C / 50% RH	1.2	%	Sim. to ISO 62
Injection Molding			
Drying Temperature	100	°C	4 hours
Melt Temperature	310 - 340	°C	-
Mould Temperature	120 - 150	°C	-

Revised: 06/26/2024

Sogun® provided information about the product, whether data, recommendations or other information, is researched and trustworthy. Since there are many influencing factors in the production process, users are advised to conduct their own tests before production. The standard values are for reference only and should not be regarded as binding specifications.

Find more information or contact us at www.sogun.com